



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[05W44831]
 Machine Id
KLEE MC110I K117-0048
 Component
Right Final Drive
 Fluid
JOHN DEERE GL-5 80W90 (6 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0199506	JR0187510	JR0174666
Sample Date		Client Info		12 Feb 2024	22 Sep 2023	19 May 2023
Machine Age	hrs	Client Info		2495	1945	1466
Oil Age	hrs	Client Info		550	1077	1042
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

PQ		ASTM D8184		244	389	476
Iron	ppm	ASTM D5185m	>500	117	248	240
Chromium	ppm	ASTM D5185m	>10	3	6	7
Nickel	ppm	ASTM D5185m	>10	<1	<1	1
Titanium	ppm	ASTM D5185m		2	2	2
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	17	2	<1
Lead	ppm	ASTM D5185m	>25	<1	0	0
Copper	ppm	ASTM D5185m	>50	3	4	3
Tin	ppm	ASTM D5185m	>10	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION






There is no indication of any contamination in the fluid.

Silicon	ppm	ASTM D5185m	>75	38	4	4
Potassium	ppm	ASTM D5185m	>20	4	1	3
Water		WC Method	>0.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	LIGHT	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the fluid is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		2	3	3
Boron	ppm	ASTM D5185m		11	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		3	6	7
Magnesium	ppm	ASTM D5185m		9	1	5
Calcium	ppm	ASTM D5185m		25	56	59
Phosphorus	ppm	ASTM D5185m		368	227	252
Zinc	ppm	ASTM D5185m		4	3	6
Sulfur	ppm	ASTM D5185m		20199	27757	25056
Visc @ 40°C	cSt	ASTM D445		137	126	▲ 127



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0199506 **Received** : 14 Feb 2024
Lab Number : 06089727 **Tested** : 16 Feb 2024
Unique Number : 10877172 **Diagnosed** : 16 Feb 2024 - Sean Felton
Test Package : CONST (Additional Tests: PQ)

JRE - MANASSAS PARK
 9107 OWENS DRIVE
 MANASSAS PARK, VA
 US 20111
 Contact: DON VEST
 dvest@jamesriverequipment.com
 T: (703)631-8500
 F: (703)631-4715

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)