**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 



## Machine Id LIEBHERR LH30M 1253-146764


LIEBHERR LH30M 1253-140 Component Front Bight Wheel Hub	b/64						
Front Right Wheel Hub {not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	OOW	Client Info	LIIIIUAUII	LH0276515		
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Date		Client Info		08 Feb 2024		
	Machine Age	hrs	Client Info		1019		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1113	Client Info		Not Changd		
	Filter Changed		Client Info		Not Change		
	Sample Status		Chefft IIIIO		NORMAL		
WEAR	Iron	ppm	ASTM D5185m	~450	43		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel		ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>4	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum		ASTM D5185m	<b>.</b> 15	<1		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		11		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal		*Visual	NONE	NONE		
	reliow ivietal	scalar	visuai	NONE			
CONTAMINATION	Silicon	ppm	ASTM D5185m	>60	4		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		10		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		51		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		7		
	Calcium	ppm	ASTM D5185m		1700		
	Phosphorus	ppm	ASTM D5185m		787		
	Zinc	ppm	ASTM D5185m		746		
	Sulfur	ppm	ASTM D5185m		9884		

Visc @ 40°C

cSt

ASTM D445

88.9





Laboratory Sample No.

: LH0276515 Lab Number : 06089751 Unique Number: 10877196 Test Package : MOBCE

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 14 Feb 2024 : 16 Feb 2024 **Tested** 

: 16 Feb 2024 - Wes Davis Diagnosed

TRAM CONSTRUCTION

9279 E KY 8 GARRISON, KY US 41141

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: