WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id

RO 91035

Center Right Genset

ECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WC0824094		
	Sample Date		Client Info		12 Feb 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
/EAR	Iron	ppm	ASTM D5185m	>50	10		
	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>5	0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		1		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
ONTAMINATION	Silicon	nnm	ASTM D5185m	. 25	4		
ONTAIVIINATION	Potassium	ppm	ASTM D5185m		0		
There is no indication of any contamination in the oil.	Fuel	ppm			_		
			WC Method		<1.0 NEG		
	Water Glycol		WC Method WC Method	>0.1			
	Soot %	%	*ASTM D7844		NEG 0		
	Nitration	Abs/cm	*ASTM D7624	>20	5.1		
	Sulfation	Abs/.1mm	*ASTM D7024		16.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
			*Visual	NORML	NORML		
	Appearance Odor	scalar scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.1	NEG		
	Linuisineu water	Scalai	visuai	>0.1			
LUID CONDITION	Sodium	ppm	ASTM D5185m		4		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		66		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		43		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		874		
	Calcium	ppm	ASTM D5185m		661		
	Phosphorus	ppm	ASTM D5185m		674		
	Zinc	ppm	ASTM D5185m		911		
	Sulfur	ppm	ASTM D5185m		2266		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	10.0		
	Base Number (BN)	mg KOH/g	ASTM D2896		6.7		
	Visc @ 100°C	cSt	ASTM D445	10.0	13.3		







Laboratory Sample No.

Lab Number : 06097389

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0824094

Unique Number : 10890242

Received : 22 Feb 2024 **Tested**

Diagnosed Test Package : MOB 1 (Additional Tests: TBN)

: 23 Feb 2024 : 24 Feb 2024 - Don Baldridge

Contact: OSCAR ROMERO oromero@atelbus.com T:

ATEL BUS & TRUCK

12120 CONWAY RD

BELTSVILLE, MD

US 20705

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)