



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**910065**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0104350</b>	GFL0110095	GFL0104394
Sample Date		Client Info		<b>19 Feb 2024</b>	07 Feb 2024	28 Dec 2023
Machine Age	hrs	Client Info		<b>6320</b>	6319	6318
Oil Age	hrs	Client Info		<b>600</b>	600	6318
Filter Age	hrs	Client Info		<b>600</b>	600	6318
Oil Changed		Client Info		<b>Changed</b>	Changed	N/A
Filter Changed		Client Info		<b>Changed</b>	Changed	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>18</b>	51	16
Chromium	ppm	ASTM D5185m	>20	<b>5</b>	1	<1
Nickel	ppm	ASTM D5185m	>5	<b>&lt;1</b>	1	0
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	<1	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	3	2
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	5	<1
Copper	ppm	ASTM D5185m	>330	<b>2</b>	10	<1
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	2	<1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>13</b>	6	3
Potassium	ppm	ASTM D5185m	>20	<b>4</b>	<1	2
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.1</b>	1	0.6
Nitration	Abs/cm	*ASTM D7624	>20	<b>4.8</b>	12.3	11.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>20.5</b>	24.8	22.0
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>6</b>	7	5
Boron	ppm	ASTM D5185m	0	<b>63</b>	2	2
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>37</b>	60	53
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	1	<1
Magnesium	ppm	ASTM D5185m	1010	<b>476</b>	914	860
Calcium	ppm	ASTM D5185m	1070	<b>1566</b>	1030	946
Phosphorus	ppm	ASTM D5185m	1150	<b>849</b>	988	963
Zinc	ppm	ASTM D5185m	1270	<b>1067</b>	1233	1167
Sulfur	ppm	ASTM D5185m	2060	<b>2678</b>	2110	2678
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>17.3</b>	24.8	21.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>10.1</b>	3.7	7.1
Visc @ 100°C	cSt	ASTM D445	15.4	<b>12.8</b>	13.7	12.8



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0104350  
**Lab Number** : 06097517  
**Unique Number** : 10890370  
**Test Package** : FLEET

**Received** : 22 Feb 2024  
**Tested** : 23 Feb 2024  
**Diagnosed** : 24 Feb 2024 - Don Baldrige

**GFL Environmental - 410 - Michigan West**  
 39000 Van Born Rd  
 Wayne, MI  
 US 48184

Contact: Belal Dgheish  
 bdgheish@gflenv.com

T: (734)714-2340

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)