



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JACKY ONEAL (S/N 74-K1-1035)
Component
Center Main Engine
Fluid
CHEVRON DELO 710 LS (350 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0066567	MW0066557	MW0055767
Sample Date		Client Info		15 Feb 2024	24 Jan 2024	15 Dec 2023
Machine Age	hrs	Client Info		9213	8832	7882
Oil Age	hrs	Client Info		9213	0	7882
Filter Age	hrs	Client Info		628	237	676
Oil Changed		Client Info		Not Chngd	N/A	Not Chngd
Filter Changed		Client Info		Changed	N/A	None
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	11	12	4
Chromium	ppm	ASTM D5185m	>8	<1	1	1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	2	2
Lead	ppm	ASTM D5185m	>18	9	2	0
Copper	ppm	ASTM D5185m	>80	7	9	3
Tin	ppm	ASTM D5185m	>14	4	5	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	3	3	0
Potassium	ppm	ASTM D5185m	>20	247	24	16
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.4	7.7	7.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	14.0	15.7	15.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	43	5	0
Boron	ppm	ASTM D5185m		35	53	35
Barium	ppm	ASTM D5185m		0	2	4
Molybdenum	ppm	ASTM D5185m		73	69	46
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		11	13	18
Calcium	ppm	ASTM D5185m		3269	4464	3497
Phosphorus	ppm	ASTM D5185m		0	43	26
Zinc	ppm	ASTM D5185m		0	0	4
Sulfur	ppm	ASTM D5185m		2166	2817	2421
Oxidation	Abs/.1mm	*ASTM D7414	>25	7.1	8.2	8.0
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	5.9	6.8	6.6
Visc @ 100°C	cSt	ASTM D445	15.5	14.6	14.8	14.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0066567
Lab Number : 06097547
Unique Number : 10890400
Test Package : MAR 2

Received : 22 Feb 2024
Tested : 23 Feb 2024
Diagnosed : 23 Feb 2024 - Wes Davis

AMERICAN COMMERCIAL LINES
 PO BOX 610, 1701 E. MARKET STREET
 JEFFERSONVILLE, IN
 US 47130
 Contact: RONALD SCHNEIDER
 ronald.schneider@bargeacbl.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (812)288-1644