



WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE B-145 (S/N 1FF245GXLMF802192)

Component
Hydraulic System

Fluid
HITACHI HYDRAULIC SUPER EX 46HN (--- GAL)

RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0203299	JR0195847	JR0123274
Sample Date		Client Info		21 Feb 2024	29 Dec 2023	25 Apr 2022
Machine Age	hrs	Client Info		3826	3597	271
Oil Age	hrs	Client Info		3826	3597	271
Filter Age	hrs	Client Info		3826	3597	271
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Not Chngd	Changed
Sample Status				ABNORMAL	ABNORMAL	ATTENTION

WEAR

All component wear rates are normal.

PQ	UOM	Method	Limit/Abn	Current	History1	History2
PQ		ASTM D8184	>50	17	16	11
Iron	ppm	ASTM D5185m	>32	6	8	2
Chromium	ppm	ASTM D5185m	>9	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	<1
Aluminum	ppm	ASTM D5185m	>9	<1	2	<1
Lead	ppm	ASTM D5185m	>28	0	<1	0
Copper	ppm	ASTM D5185m	>50	3	4	2
Tin	ppm	ASTM D5185m	>5	<1	1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is a high amount of particulates present in the oil.

Silicon	ppm	ASTM D5185m	>11	1	4	<1
Potassium	ppm	ASTM D5185m	>20	0	1	0
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	22891	---	5590
Particles >6µm		ASTM D7647	>20000	10080	---	2709
Particles >14µm		ASTM D7647	>640	▲ 2108	---	▲ 703
Particles >21µm		ASTM D7647	>160	▲ 846	---	151
Particles >38µm		ASTM D7647	>40	▲ 52	---	6
Particles >71µm		ASTM D7647	>10	4	---	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	▲ 22/21/18	---	▲ 20/19/17
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	▲ MODER	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	<1	0	0
Boron	ppm	ASTM D5185m		0	0	1
Barium	ppm	ASTM D5185m		0	8	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		0	<1	0
Calcium	ppm	ASTM D5185m		5	7	1
Phosphorus	ppm	ASTM D5185m	827	430	510	611
Zinc	ppm	ASTM D5185m	0	16	14	26
Sulfur	ppm	ASTM D5185m	13	1118	656	144
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.269	0.20	0.25
Visc @ 40°C	cSt	ASTM D445	47	45.3	45.5	46.4



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0203299 **Received** : 22 Feb 2024
Lab Number : 06097607 **Tested** : 23 Feb 2024
Unique Number : 10890460 **Diagnosed** : 24 Feb 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

JRE - MANASSAS PARK
 9107 OWENS DRIVE
 MANASSAS PARK, VA
 US 20111
 Contact: RED AUZENNE
 red.auzenne@jamesriverequipment.com
 T:
 F: (703)631-4715

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)