

Area



[HANSON AGGREGATES VA] CATERPILLAR 962K C205537 (S/N 962KHFLL00354)

Front Differential

TDTO FLUID SAE 50 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) TDTO FLUID SAE 50. Please confirm.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0194935		
Sample Date		Client Info		20 Feb 2024		
Machine Age	hrs	Client Info		14350		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
PQ		ASTM D8184		142		
Iron	ppm	ASTM D5185m	>500	261		
Chromium	ppm	ASTM D5185m	>3	1		
Nickel	ppm	ASTM D5185m	>3	1		
Titanium	ppm	ASTM D5185m	>2	2		
Silver	ppm	ASTM D5185m	>2	<1		
Aluminum	ppm	ASTM D5185m	>30	2		
Lead	ppm	ASTM D5185m	>13	2		
Copper	ppm	ASTM D5185m	>103	33		
Tin	ppm	ASTM D5185m	>5	2		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	nnm	ASTM D5185m	>100	19		
Potassium	ppm	ASTM D5185m	>20	2		
Water	ppm	WC Method	>.2	2 NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
	scalar	*Visual	NORML	NORML		
Appearance Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
	Scala	visuai	>.∠	NEG		
Sodium	ppm	ASTM D5185m		•		
	1. 1	ACTIVI DOTOCITI		0		
Boron	ppm	ASTM D5185m	37	0 <1		
Boron Barium			37 7			
	ppm	ASTM D5185m		<1		
Barium	ppm ppm	ASTM D5185m ASTM D5185m	7	<1 5		
Barium Molybdenum	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	7	<1 5 1		
Barium Molybdenum Manganese	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	7 5	<1 5 1 3		
Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	7 5 40	<1 5 1 3 12		
Barium Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	7 5 40 2650	<1 5 1 3 12 2914		
Barium Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	7 5 40 2650 1050	<1 5 1 3 12 2914 969		
Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m	7 5 40 2650 1050 1075	<1 5 1 3 12 2914 969 1238		

Contact/Location: PHIL DAUGHERTY - JAMWIN





JRE - STEPHENSON Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : JR0194935 Received : 22 Feb 2024 245 YARDMASTER COURT Lab Number : 06097954 : 23 Feb 2024 STEPHENSON, VA Tested Unique Number : 10896184 : 23 Feb 2024 - Wes Davis US 22656-1761 Diagnosed Test Package : CONST (Additional Tests: PQ) Contact: PHIL DAUGHERTY Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. pdaugherty@jamesriverequipment.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: x: F: (540)693-2588 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

ĕ

Contact/Location: PHIL DAUGHERTY - JAMWIN