



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
2126978

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 10W30 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0118398	PCA0099526	PCA0101146
Sample Date		Client Info		12 Feb 2024	09 Dec 2023	26 Oct 2023
Machine Age	mls	Client Info		0	20000	0
Oil Age	mls	Client Info		0	20000	0
Filter Age	mls	Client Info		0	20000	0
Oil Changed		Client Info		N/A	Not Changd	N/A
Filter Changed		Client Info		N/A	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	25	15	0
Chromium	ppm	ASTM D5185m	>20	<1	<1	0
Nickel	ppm	ASTM D5185m	>4	2	2	0
Titanium	ppm	ASTM D5185m		4	<1	<1
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>20	10	6	2
Lead	ppm	ASTM D5185m	>40	1	1	<1
Copper	ppm	ASTM D5185m	>330	34	27	5
Tin	ppm	ASTM D5185m	>15	2	1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	5	5
Potassium	ppm	ASTM D5185m	>20	25	17	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.3	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.8	8.1	4.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	19.2	17.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	0	<1
Boron	ppm	ASTM D5185m	2	4	0	6
Barium	ppm	ASTM D5185m	0	0	11	0
Molybdenum	ppm	ASTM D5185m	50	55	57	53
Manganese	ppm	ASTM D5185m	0	1	<1	<1
Magnesium	ppm	ASTM D5185m	950	820	884	874
Calcium	ppm	ASTM D5185m	1050	1054	1046	1003
Phosphorus	ppm	ASTM D5185m	995	847	913	984
Zinc	ppm	ASTM D5185m	1180	1122	1170	1162
Sulfur	ppm	ASTM D5185m	2600	2453	3359	2923
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.3	15.2	13.0
Base Number (BN)	mg KOH/g	ASTM D2896		5.7	7.3	9.3
Visc @ 100°C	cSt	ASTM D445	12.00	11.1	11.3	11.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0118398
Lab Number : 06098153
Unique Number : 10896383
Test Package : FLEET

Received : 23 Feb 2024
Tested : 25 Feb 2024
Diagnosed : 25 Feb 2024 - Wes Davis

PERDUE FARMS - SALISBURY
 7036 ZION CHURCH ROAD
 SALISBURY, MD
 US 21802

Contact: RICHARD O'NEAL
 richard.oneal@perdue.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (410)543-3628
 F: (410)341-2164