



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH T800 3909 (S/N KCB65350)

Component
Diesel Engine

Fluid
SHELL ROTELLA T4 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0878922	WC0822267	WC0613635
Sample Date		Client Info		21 Feb 2024	03 Nov 2023	21 Jul 2023
Machine Age	mls	Client Info		990772	970011	939759
Oil Age	mls	Client Info		0	12000	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	76	56	▲ 141
Chromium	ppm	ASTM D5185m	>20	1	<1	2
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	2	2
Lead	ppm	ASTM D5185m	>40	2	2	8
Copper	ppm	ASTM D5185m	>330	6	4	12
Tin	ppm	ASTM D5185m	>15	2	<1	3
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	6	10
Potassium	ppm	ASTM D5185m	>20	0	2	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.1	0.9	1.5
Nitration	Abs/cm	*ASTM D7624	>20	9.7	8.2	11.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.1	20.6	25.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	8
Boron	ppm	ASTM D5185m		13	15	8
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		46	56	66
Manganese	ppm	ASTM D5185m		<1	0	1
Magnesium	ppm	ASTM D5185m		513	637	903
Calcium	ppm	ASTM D5185m		1654	1452	1403
Phosphorus	ppm	ASTM D5185m		926	913	1070
Zinc	ppm	ASTM D5185m		1014	1228	1322
Sulfur	ppm	ASTM D5185m		2794	3211	3213
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.1	15.6	21.9
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	6.3	8.0	5.9
Visc @ 100°C	cSt	ASTM D445	15	14.7	14.2	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0878922 **Received** : 23 Feb 2024
Lab Number : 06098266 **Tested** : 26 Feb 2024
Unique Number : 10896496 **Diagnosed** : 26 Feb 2024 - Don Baldrige
Test Package : MOB 1 (Additional Tests: TBN)

JOHNSON BREEDERS
 3425 HWY 117N
 ROSE HILL, NC
 US 28458
 Contact: GREG JONES
 gregory.jones@houseofraeford.com
 T: (910)289-6884
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)