
**WEAR** CONTAMINATION **FLUID CONDITION**  **ABNORMAL ABNORMAL NORMAL** 

## JOHN DEERE 2038R 1LV2038RESJ103219

Component Hydraulic System

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		JR0189852		
We recommend you service the filters on this component. We recommend an early resample to monitor this condition.	Sample Date		Client Info		29 Jan 2024		
	Machine Age	hrs	Client Info		406		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
VEAR	PQ		ASTM D8184		34		
	Iron	ppm	ASTM D5185m	>20	<b>▲</b> 48		
The iron level is abnormal. All other component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m	710	<1		
	Silver	ppm	ASTM D5185m		3		
	Aluminum	ppm	ASTM D5185m	>10	<1		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		32		
	Tin	ppm	ASTM D5185m		2		
	Vanadium	ppm	ASTM D5185m	710	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	> 20	0		
ON I AMINA HON	Potassium	ppm	ASTM D5185m		8 3		
There is a high amount of particulates present in the oil.	Water	ppm	WC Method		NEG		
	Particles >4µm Particles >6µm		ASTM D7647 ASTM D7647		▲ 108717 ▲ 15449		
	Particles >14µm		ASTM D7647		▲ 209		
	Particles >14µm		ASTM D7647		<u>^</u> 209 <u>^</u> 54		
	Particles >21µm		ASTM D7647		4		
	Particles >30µm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		<u> </u>		
	Silt	000101	*Visual				
		scalar		NONE	NONE LIGHT		
	Debris Sand/Dist	scalar	*Visual	NONE			
	Sand/Dirt	scalar		NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
·····	Emulsified Water	Scalar	*Visual	>0.1	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the city	Boron	ppm	ASTM D5185m		2		
The AN level is acceptable for this fluid. The condition of the oils additive package is suitable for further service.	Barium	ppm	ASTM D5185m		6		
	Molybdenum	ppm	ASTM D5185m	0	1		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		89		
	Calcium	ppm	ASTM D5185m		3127		
	Phosphorus	ppm	ASTM D5185m	1290	925		
	Zinc	ppm	ASTM D5185m	1640	1192		
	Sulfur	ppm	ASTM D5185m		3437		
	Acid Number (AN)	mg KOH/g	ASTM D8045	1.8	1.41		
	Visc @ 40°C	cSt	ASTM D445	57.0	31.8		





Certificate L2367

Laboratory Sample No.

: JR0189852 Lab Number : 06098282

Unique Number : 10896512

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

Diagnosed Test Package : CONST ( Additional Tests: PQ )

: 28 Feb 2024 : 28 Feb 2024 - Jonathan Hester

: 23 Feb 2024

38431 HWY 58 LA CROSSE, VA US 23950-1807

Contact: HUNTER GREEN hgreen@jamesriverequipment.com T: (434)447-4325

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (434)447-1329