WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Ic

JOHN DEERE 843L 1DW843LBKMF710970

Component Front Differential

JOHN DEERE HY-GARD HYD/TRANS (--- QTS)

JOHN DEERE HY-GARD HYD/TRANS (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WE0006267	WE0000296	
	Sample Date		Client Info		22 Feb 2024	08 Aug 2021	
	Machine Age	hrs	Client Info		5817	539	
	Oil Age	hrs	Client Info		0	539	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		N/A	Not Changd	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184		11		
	Iron	ppm	ASTM D5185m	>500	0	260	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0	2	
	Nickel	ppm	ASTM D5185m		<1	<1	
	Titanium	ppm	ASTM D5185m		0	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	1	2	
	Lead	ppm	ASTM D5185m		0	4	
	Copper	ppm	ASTM D5185m		0	13	
	Tin	ppm	ASTM D5185m	>10	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	5	11	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0	2	
	Water		WC Method	>.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	LIGHT	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	3	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	<1	5	
	Barium	ppm	ASTM D5185m	0	0	3	
	Molybdenum	ppm	ASTM D5185m	0	0	<1	
	Manganese	ppm	ASTM D5185m		<1	6	
	Magnesium	ppm	ASTM D5185m	145	107	114	
	Calcium	ppm	ASTM D5185m	3570	3318	3948	
	Phosphorus	ppm	ASTM D5185m	1290	1001	1119	
	Zinc	ppm	ASTM D5185m	1640	1265	1279	
	Sulfur	ppm	ASTM D5185m		3477	3756	





Certificate L2367

Report Id: WARNOR [WUSCAR] 06098670 (Generated: 02/26/2024 13:41:58) Rev: 1

Laboratory Sample No.

Lab Number : 06098670

: WE0006267

Unique Number : 10896900

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 23 Feb 2024 **Tested** : 26 Feb 2024 Diagnosed

: 26 Feb 2024 - Wes Davis

WARRIOR TRACTOR AND EQUIPMENT - NORTHPORT P.O. BOX 412 NORTHPORT, AL US 35476

Contact: SCOTT GOOD sgood@warriortractor.com

T: (205)339-0300

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Test Package : CONST (Additional Tests: PQ)

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: SCOTT GOOD - WARNOR