



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[2799-2]
 Machine Id
MECALAC 6MCR 0152243
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL 10W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (check for damage).

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP445936	---	---
Sample Date		Client Info		19 Feb 2024	---	---
Machine Age	hrs	Client Info		42	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Not Changd	---	---
Filter Changed		Client Info		N/A	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	26	---	---
Chromium	ppm	ASTM D5185m	>20	1	---	---
Nickel	ppm	ASTM D5185m	>4	0	---	---
Titanium	ppm	ASTM D5185m		<1	---	---
Silver	ppm	ASTM D5185m	>3	0	---	---
Aluminum	ppm	ASTM D5185m	>20	9	---	---
Lead	ppm	ASTM D5185m	>40	0	---	---
Copper	ppm	ASTM D5185m	>330	11	---	---
Tin	ppm	ASTM D5185m	>15	<1	---	---
Vanadium	ppm	ASTM D5185m		0	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	24	---	---
Potassium	ppm	ASTM D5185m	>20	2	---	---
Fuel		WC Method	>5	<1.0	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>3	0.3	---	---
Nitration	Abs/cm	*ASTM D7624	>20	8.6	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.6	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---

FLUID CONDITION

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

Sodium	ppm	ASTM D5185m		2	---	---
Boron	ppm	ASTM D5185m	250	123	---	---
Barium	ppm	ASTM D5185m	10	<1	---	---
Molybdenum	ppm	ASTM D5185m	100	51	---	---
Manganese	ppm	ASTM D5185m		3	---	---
Magnesium	ppm	ASTM D5185m	450	511	---	---
Calcium	ppm	ASTM D5185m	3000	1676	---	---
Phosphorus	ppm	ASTM D5185m	1150	1062	---	---
Zinc	ppm	ASTM D5185m	1350	1218	---	---
Sulfur	ppm	ASTM D5185m	4250	4110	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.3	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	5.7	---	---
Visc @ 100°C	cSt	ASTM D445	14.4	13.4	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP445936 **Received** : 23 Feb 2024
Lab Number : 06098871 **Tested** : 26 Feb 2024
Unique Number : 10897101 **Diagnosed** : 26 Feb 2024 - Don Baldrige
Test Package : MOB 1 (Additional Tests: TBN)

MCCLUNG-LOGAN EQUIPMENT CO - BRIDGEVILLE
 17941 SUSSEX HIGHWAY
 BRIDGEVILLE, DE
 US 19933
 Contact: MATT CLARK
 MCLARK@mcclung-logan.com
 T: (302)337-3400
 F: (302)337-9083

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)