



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH 3055
Component
Diesel Engine
Fluid
CHEVRON DELO 400 XLE 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0833243	WC0833199	WC0702424
Sample Date		Client Info		11 Jan 2024	23 Sep 2023	25 May 2023
Machine Age	mls	Client Info		411366	374715	336600
Oil Age	mls	Client Info		36653	38053	47400
Filter Age	mls	Client Info		36653	38053	47400
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	13	16	25
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	2	2
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	5	5	6
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>330	7	7	6
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	9	8	7
Potassium	ppm	ASTM D5185m	>20	14	15	15
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.6	0.7
Nitration	Abs/cm	*ASTM D7624	>20	9.9	9.8	10.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.0	23.5	23.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		58	73	63
Boron	ppm	ASTM D5185m		20	24	22
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		9	12	8
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		804	773	746
Calcium	ppm	ASTM D5185m	2900	1447	1356	1378
Phosphorus	ppm	ASTM D5185m	1100	718	725	725
Zinc	ppm	ASTM D5185m	1200	847	882	873
Sulfur	ppm	ASTM D5185m	4000	3107	3375	3023
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.3	17.9	17.3
Base Number (BN)	mg KOH/g	ASTM D2896	10.3	5.9	6.0	6.4
Visc @ 100°C	cSt	ASTM D445	11.9	11.6	12.0	11.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0833243
Lab Number : 06098944
Unique Number : 10897174
Test Package : FLEET

Received : 23 Feb 2024
Tested : 26 Feb 2024
Diagnosed : 26 Feb 2024 - Wes Davis

LTI/MILKY WAY - MOSES
 120 WISER LANE
 MOSES LAKE, WA
 US 98837

Contact: MIGUEL PEREZ
 mperex@lynden.com; dougb@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (509)765-5840
 F: (500)765-5636