



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[05W44928]

Machine Id

JOHN DEERE 350P 1FF350PALPF000489

Component

Hydraulic System

Fluid

HITACHI HYDRAULIC SUPER EX 46HN (220 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0202979	JR0192226	JR0181791
Sample Date		Client Info		22 Feb 2024	25 Oct 2023	26 Jul 2023
Machine Age	hrs	Client Info		1493	941	469
Oil Age	hrs	Client Info		1493	941	469
Filter Age	hrs	Client Info		552	0	469
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Not Chngd	Changed	Not Chngd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	15	15	13
Iron	ppm	ASTM D5185m	>32	2	3	2
Chromium	ppm	ASTM D5185m	>9	0	0	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	0	0	0
Lead	ppm	ASTM D5185m	>28	0	0	0
Copper	ppm	ASTM D5185m	>50	1	3	4
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>11	<1	1	<1
Potassium	ppm	ASTM D5185m	>20	0	<1	1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	17739	2449	3494
Particles >6µm		ASTM D7647	>20000	891	685	765
Particles >14µm		ASTM D7647	>640	10	98	63
Particles >21µm		ASTM D7647	>160	3	31	17
Particles >38µm		ASTM D7647	>40	1	1	1
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	21/17/10	18/17/14	19/17/13
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	0	2	1
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		<1	0	<1
Calcium	ppm	ASTM D5185m		2	2	0
Phosphorus	ppm	ASTM D5185m	827	518	458	603
Zinc	ppm	ASTM D5185m	0	18	31	22
Sulfur	ppm	ASTM D5185m	13	79	109	90
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.22	0.15	0.13
Visc @ 40°C	cSt	ASTM D445	47	46.1	45.9	45.9



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0202979 **Received** : 23 Feb 2024
Lab Number : 06099052 **Tested** : 26 Feb 2024
Unique Number : 10897282 **Diagnosed** : 26 Feb 2024 - Angela Borella
Test Package : CONST (Additional Tests: PQ)

B & S SITE DEVELOPMENT
 7800 PINEY BRANCH LANE
 BRISTOW, VA
 US 20136
 Contact: DANNY HUFF
 dhuff@bandssite.com
 T: (540)270-3203
 F: (703)753-0605

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)