



WEAR CHECK

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
2H28
Machine Id
PETERBILT 348 RTK6253 (S/N 2NP3XJ0X0KM622513)
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ARI06099559	ARI06033095	ARI0004237
Sample Date		Client Info		25 Feb 2024	12 Dec 2023	15 Feb 2023
Machine Age	mls	Client Info		0	98407	89434
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ATTENTION	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>110	1	4	2
Chromium	ppm	ASTM D5185m	>4	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	3	2	<1
Lead	ppm	ASTM D5185m	>45	<1	<1	0
Copper	ppm	ASTM D5185m	>85	<1	1	0
Tin	ppm	ASTM D5185m	>4	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	5	4	1
Potassium	ppm	ASTM D5185m	>20	0	3	3
Fuel		WC Method	>5	<1.0	0.7	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.2
Nitration	Abs/cm	*ASTM D7624	>20	5.2	4.2	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.4	14.8	18.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	2	<1	<1
Boron	ppm	ASTM D5185m	250	338	34	43
Barium	ppm	ASTM D5185m	10	0	11	<1
Molybdenum	ppm	ASTM D5185m	100	109	26	67
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m	450	535	93	827
Calcium	ppm	ASTM D5185m	3000	1599	2059	1158
Phosphorus	ppm	ASTM D5185m	1150	738	840	949
Zinc	ppm	ASTM D5185m	1350	835	1025	1131
Sulfur	ppm	ASTM D5185m	4250	2530	3532	2906
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	7.3	14.5
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.3	7.6	9.8
Visc @ 100°C	cSt	ASTM D445	14.4	12.7	▲ 11.2	12.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ARI06099559 **Received** : 26 Feb 2024
Lab Number : 06099559 **Tested** : 27 Feb 2024
Unique Number : 10897789 **Diagnosed** : 27 Feb 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

INSITUFORM TECHNOLOGIES, INC
 17988 EDISON AVE.
 CHESTERFIELD, MO
 US 63005
 Contact: JOHN SLOAN
 ARICHTER@INSITUFORM.COM
 T: (314)280-7555
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)