

- - - -

Machine Id 12961 Component Diesel Engine DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History	History 2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.		UOIVI		LITTIL/ADT	WC0842077	History1 WC0842117	History2
	Sample Number		Client Info				WC0742426
	Sample Date	mele	Client Info		13 Jan 2024	28 Oct 2023	10 May 2023
	Machine Age	mls	Client Info		170968	162339	145168
	Oil Age	mls	Client Info		0	0	0
	Filter Age	mls	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m	>100	13	18	41
	Chromium	ppm	ASTM D5185m		<1	2	1
	Nickel	ppm	ASTM D5185m		0	0	<1
	Titanium	ppm	ASTM D5185m		<1	<1	<1
	Silver	ppm	ASTM D5185m	>3	0	0	0
	Aluminum	ppm	ASTM D5185m		4	5	4
	Lead	ppm	ASTM D5185m		0	1	0
	Copper	ppm	ASTM D5185m		1	5	2
	Tin	ppm	ASTM D5185m		0	0	0
	Vanadium	ppm	ASTM D5185m		0	<1	<1
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m		7	18	6
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1	4	3
	Fuel		WC Method		<1.0	<1.0	<1.0
	Water		WC Method	>0.2	NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	0.2	0.2	0.5
	Nitration	Abs/cm	*ASTM D7624	>20	9.6	12.1	13.7
	Sulfation	Abs/.1mm	*ASTM D7415		23.3	23.3	31.1
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	<u>\158</u>	3	3	3
T LOID CONDITION	Boron	ppm	ASTM D5185m		242	41	3
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		<1	0	0
	Molybdenum	ppm	ASTM D5185m		80	79	102
	Manganese	ppm	ASTM D5185m	100	<1	<1	<1
	Magnesium	ppm	ASTM D5185m	450	528	296	1608
	Calcium	ppm	ASTM D5185m		1343	1783	1802
	Phosphorus	ppm	ASTM D5185m	1150	1010	830	1010
	Phosphorus Zinc	ppm ppm	ASTM D5185m ASTM D5185m		1018 1192	830 1206	1610 1955

Sulfur

Oxidation

Visc @ 100°C cSt

3547

22.5

6.3

14.0

3005

20.0

6.8

13.3

ppm ASTM D5185m 4250

Abs/.1mm *ASTM D7414 >25

ASTM D445 14.4


Base Number (BN) mg KOH/g ASTM D2896 8.5

3885

11.3

26.9

14.7



* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: Audrey Hopkins - SALWIN

F: x:

T: (336)767-9642