



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
Store 5 - Cross Lanes [RO#147149]
Machine Id
JOHN DEERE 1050K 1T01050PCJF323379
Component
Hydraulic System
Fluid
JOHN DEERE HYDRAU (23 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0048645	LEC0035504	LECP187436
Sample Date		Client Info		22 Feb 2024	08 Jun 2023	30 Nov 2018
Machine Age	hrs	Client Info		1208	643	604
Oil Age	hrs	Client Info		1208	643	604
Filter Age	hrs	Client Info		1208	643	604
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	12	13	15
Iron	ppm	ASTM D5185m	>23	1	1	2
Chromium	ppm	ASTM D5185m	>9	0	0	<1
Nickel	ppm	ASTM D5185m	>5	0	<1	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	<1	0
Aluminum	ppm	ASTM D5185m	>9	0	0	0
Lead	ppm	ASTM D5185m	>28	2	0	2
Copper	ppm	ASTM D5185m	>51	8	6	3
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>31	<1	<1	1
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	2761	2702	2607
Particles >6µm		ASTM D7647	>20000	108	516	290
Particles >14µm		ASTM D7647	>640	10	43	12
Particles >21µm		ASTM D7647	>160	3	15	3
Particles >38µm		ASTM D7647	>40	0	1	0
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	19/14/10	19/16/13	19/15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	VLITE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	2	1	1
Boron	ppm	ASTM D5185m		0	0	1
Barium	ppm	ASTM D5185m		1	0	1
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m		0	0	<1
Calcium	ppm	ASTM D5185m	87	73	92	83
Phosphorus	ppm	ASTM D5185m	727	584	689	551
Zinc	ppm	ASTM D5185m	900	718	876	724
Sulfur	ppm	ASTM D5185m	1500	1458	2026	1337
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.70	0.67	0.746
Visc @ 40°C	cSt	ASTM D445	65	58.1	59.5	58.19



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0048645 **Received** : 26 Feb 2024
Lab Number : 06100060 **Tested** : 27 Feb 2024
Unique Number : 10898290 **Diagnosed** : 27 Feb 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

LESLIE EQUIPMENT COMPANY
 105 TENNIS CENTER DR.
 MARIETTA, OH
 US 45750-9765
 Contact: LEANNE KENDALL
 KendalLeanne@lec1.com
 T:
 F: (740)373-5570

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)