



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



Store 4 - Fairmont

JOHN DEERE 160G 1FF160GXENF058790

Component Pump Drive

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (1 QTS)

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (1 QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0047864	LEC0038207	
	Sample Date		Client Info		20 Feb 2024	28 Apr 2023	
	Machine Age	hrs	Client Info		925	337	
	Oil Age	hrs	Client Info		925	337	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Not Changd	
	Filter Changed		Client Info		N/A	None	
	Sample Status				NORMAL	ATTENTION	
WEAR	PQ		ASTM D8184		11	17	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>151	54	35	
	Chromium	ppm	ASTM D5185m		<1	<1	
	Nickel	ppm	ASTM D5185m	>10	0	<1	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>21	4	2	
	Lead	ppm	ASTM D5185m	>51	1	0	
	Copper	ppm	ASTM D5185m	>51	2	1	
	Tin	ppm	ASTM D5185m	>4	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>31	13	11	
	Potassium	ppm	ASTM D5185m	>20	2	2	
	Water		WC Method	>0.1	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	5	4	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		62	63	
	Barium	ppm	ASTM D5185m		5	4	
	Molybdenum	ppm	ASTM D5185m		104	105	
	Manganese	ppm	ASTM D5185m		4	4	
	Magnesium	ppm	ASTM D5185m		18	1 7	
	Calcium	ppm	ASTM D5185m		4093	4203	
	Phosphorus	ppm	ASTM D5185m		1174	1206	
	Zinc	ppm	ASTM D5185m		1389	1398	
	Sulfur	ppm	ASTM D5185m		7707	9878	







Certificate L2367

Laboratory Sample No.

Lab Number : 06100336 Unique Number: 10898566

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0047864

Received **Tested** Diagnosed

: 27 Feb 2024 : 28 Feb 2024 - Don Baldridge

: 26 Feb 2024

Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

US 45750-9765 Contact: LEANNE KENDALL

KendalLeanne@lec1.com

105 TENNIS CENTER DR.

LESLIE EQUIPMENT COMPANY

T: F: (740)373-5570

MARIETTA, OH

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)