

WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL ATTENTION



## **VOLVO A40G 353407**

Component Drop Box

MOBIL MOBILUBE HD 80W9	) ( GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		VCP416820		
	Sample Date		Client Info		13 Feb 2024		
	Machine Age	hrs	Client Info		1268		
	Oil Age	hrs	Client Info		871		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				ATTENTION		
WEAR	Iron	ppm	ASTM D5185m	>500	65		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	<1		
	Lead	ppm	ASTM D5185m	>30	1		
	Copper	ppm	ASTM D5185m	>30	7		
	Tin	ppm	ASTM D5185m	>20	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	47		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	4		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		8		
The oil viscosity is lower than normal. Additive levels indicate the addition of a different brand, or type of oil. Confirm oil type.	Boron	ppm	ASTM D5185m		139		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		10		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		<b>5</b> 0		
	Phosphorus	ppm	ASTM D5185m		<u> </u>		
	Zinc	ppm	ASTM D5185m		72		
	Sulfur	ppm	ASTM D5185m	105	24121		
	Visc @ 40°C	cSt	ASTM D445	136	52.0		





Certificate L2367

Laboratory Sample No.

: VCP416820 Lab Number : 06100407 Unique Number: 10898637 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 26 Feb 2024 **Tested** : 27 Feb 2024

: 28 Feb 2024 - Jonathan Hester Diagnosed

SCHILDBERG CONSTRUCTION COMPANY PO BOX 358

GREENFIELD, IA US 50849

Contact: SCOTT ARMSTRONG sarmstrong@schildberg.com

T: (641)743-8237 F: (641)743-2486

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)