WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL


Machine Id


CR1216 - OUTER


Component Rear Right Final Drive

GEAR OIL ISO 220 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0873281	WC0809253	
	Sample Date		Client Info		17 Feb 2024	02 May 2023	
	Machine Age	hrs	Client Info		3481	2737	
	Oil Age	hrs	Client Info		0	763	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Not Changd	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>500	6	4	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0	0	
	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	0	0	
	Lead	ppm	ASTM D5185m		1	<1	
	Copper	ppm	ASTM D5185m	>50	<1	<1	
	Tin	ppm	ASTM D5185m	>10	0	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION						,	
CONTAMINATION	Silicon	ppm	ASTM D5185m		<1	1	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0	<1	
	Water		WC Method	>0.2	NEG	NEG	
	Silt Debris	scalar	*Visual *Visual	NONE	NONE NONE	NONE NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water		*Visual	>0.2	NEG	NEG	
			• • • • • • • • • • • • • • • • • • •			INCO	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	0	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	50	3	2	
	Barium	ppm	ASTM D5185m	15	0	0	
	Molybdenum	ppm	ASTM D5185m	15	0	0	
	Manganese	ppm	ASTM D5185m		<1	0	
	Magnesium	ppm	ASTM D5185m	50	0	<1	
	Calcium	ppm	ASTM D5185m		1	1	
	Phosphorus	ppm	ASTM D5185m		374	386	
	Zinc	ppm	ASTM D5185m		0	1	
	Sulfur	ppm	ASTM D5185m		5112	5835	
	Visc @ 40°C	cSt	ASTM D445	220	213	213	











Certificate L2367

Laboratory Sample No.

: WC0873281 Lab Number : 06100491 Unique Number : 10898721 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 26 Feb 2024 **Tested** : 27 Feb 2024

Diagnosed : 27 Feb 2024 - Wes Davis **BUCKNER HEAVY LIFT** 4732 NC 54 EAST

GRAHAM, NC US 27253-9215

Contact: MICHAEL LAWSON michaell@bucknercompanies.com

T: (336)376-8888 F: (336)376-4090

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)