



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
(ZKZ1622)
Machine Id
828044-Pete 520
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (42 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0096512	GFL0096488	GFL0096491
Sample Date		Client Info		20 Feb 2024	05 Dec 2023	20 Nov 2023
Machine Age	hrs	Client Info		11846	11323	11256
Oil Age	hrs	Client Info		585	555	488
Filter Age	hrs	Client Info		0	555	488
Oil Changed		Client Info		Changed	Not Changed	Changed
Filter Changed		Client Info		Changed	Not Changed	Changed
Sample Status				NORMAL	NORMAL	MARGINAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>165	4	4	9
Chromium	ppm	ASTM D5185m	>5	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m	>2	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	2	<1
Lead	ppm	ASTM D5185m	>150	2	0	1
Copper	ppm	ASTM D5185m	>90	3	1	7
Tin	ppm	ASTM D5185m	>5	0	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>35	5	4	6
Potassium	ppm	ASTM D5185m	>20	2	1	3
Fuel		WC Method	>3.0	<1.0	<1.0	▲ 1.1
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>7.5	0.3	0.1	0.4
Nitration	Abs/cm	*ASTM D7624	>20	8.4	5.4	8.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	17.9	19.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		7	5	8
Boron	ppm	ASTM D5185m	0	10	13	15
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	68	61	55
Manganese	ppm	ASTM D5185m	0	<1	0	0
Magnesium	ppm	ASTM D5185m	1010	1074	931	919
Calcium	ppm	ASTM D5185m	1070	1303	1086	1105
Phosphorus	ppm	ASTM D5185m	1150	1179	978	963
Zinc	ppm	ASTM D5185m	1270	1427	1226	1239
Sulfur	ppm	ASTM D5185m	2060	3210	3158	2536
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.3	13.6	15.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.7	8.8	7.5
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	14.1	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0096512
Lab Number : 06100647
Unique Number : 10898877
Test Package : FLEET

Received : 26 Feb 2024
Tested : 27 Feb 2024
Diagnosed : 27 Feb 2024 - Wes Davis

GFL Environmental - 656 - Culpeper Hauling
 15490 Montanus Drive
 Culpeper, VA
 US 22701
 Contact: Matt Hanna
 mhanna@gflenv.com
 T: (540)727-0887
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)