



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
KEMP QUARRIES / BCS - GRAVETTE [67745]
Machine Id
WL124
Component
Rear Differential
Fluid
PETRO CANADA PRODURO TO-4 SAE 50 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: Pm3)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0069791	PCA0086997	PCA0084631
Sample Date		Client Info		08 Feb 2024	12 Oct 2023	06 Jul 2023
Machine Age	hrs	Client Info		37365	37365	36752
Oil Age	hrs	Client Info		36319	37365	36752
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	51	33	46
Chromium	ppm	ASTM D5185m	>3	<1	<1	<1
Nickel	ppm	ASTM D5185m	>3	0	0	<1
Titanium	ppm	ASTM D5185m	>2	0	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	<1	2	2
Lead	ppm	ASTM D5185m	>13	0	<1	0
Copper	ppm	ASTM D5185m	>103	2	14	2
Tin	ppm	ASTM D5185m	>5	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>100	11	12	12
Potassium	ppm	ASTM D5185m	>20	0	2	2
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		0	0	2
Boron	ppm	ASTM D5185m	2	0	3	2
Barium	ppm	ASTM D5185m	0	0	9	0
Molybdenum	ppm	ASTM D5185m	0	0	2	1
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	9	17	18	19
Calcium	ppm	ASTM D5185m	3114	2539	3001	3112
Phosphorus	ppm	ASTM D5185m	1099	926	1028	1059
Zinc	ppm	ASTM D5185m	1245	1192	1230	1308
Sulfur	ppm	ASTM D5185m	7086	4805	6468	6280
Visc @ 40°C	cSt	ASTM D445	213.9	175	180	177



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0069791
Lab Number : 06101189
Unique Number : 10899419
Test Package : MOB 1

Kemp Quarries - Benton County Stone - Gravette
 15100 N Hwy 59
 Sulphur Springs, AR
 US 72768
 Contact:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

gravette@bentoncountystone.com
 T:
 F: