WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[W02008034]

VOLVO A25G 752865

Component Bogie/Center Differential

VOLVO SUPER GEAR OIL 75W-80-GO102 (10 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. (Customer Sample Comment: W02008034 1st 1000 hour service)	Sample Number		Client Info		ML0886253		
	Sample Date		Client Info		23 Feb 2024		
	Machine Age	hrs	Client Info		970		
	Oil Age	hrs	Client Info		970		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>900	276		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	6		
	Nickel	ppm	ASTM D5185m	>10	3		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	<1		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>150	17		
	Tin	ppm	ASTM D5185m	>20	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	<u> 50</u>	4		
	Potassium	ppm	ASTM D5185m		0		
There is no indication of any contamination in the oil.	Water	ррпп	WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	nnm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		254		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		6		
	Molybdenum	ppm	ASTM D5185m		4		
	Manganese	ppm	ASTM D5185m		12		
	Magnesium	ppm	ASTM D5185m		5		
	Calcium	ppm	ASTM D5185m		157		
	Phosphorus	ppm	ASTM D5185m		1264		
	Zinc	ppm	ASTM D5185m		73		
	Sulfur	ppm	ASTM D5185m		22397		
	Visc @ 40°C	cSt	ASTM D445		102		





Certificate L2367

Laboratory

Sample No.

: ML0886253 Lab Number : 06101226 Unique Number: 10899456 Test Package : MOBCE

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 26 Feb 2024 : 28 Feb 2024 **Tested**

: 28 Feb 2024 - Don Baldridge Diagnosed

MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS

8450 QUARRY ROAD MANASSAS, VA US 20110

Contact: DARRELL ANDES

dandes@mcclung-logan.com T:

Submitted By: DARRELL ANDES

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (703)393-7844