

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



W02008034] Machine Id VOLVO A25G 752865

Front Center Drop Box

VÕLVO SUPER GEAR OIL 75W-80-GO102 (3 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. (Customer Sample Comment: W02008034 1st 1000 hour service)

 _	
ΕЛ	D

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ML0886255		
Sample Date		Client Info		23 Feb 2024		
Machine Age	hrs	Client Info		970		
Oil Age	hrs	Client Info		970		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
			500			
Iron	ppm	ASTM D5185m	>500	36		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	7		
Lead	ppm	ASTM D5185m	>30	0		
Copper	ppm	ASTM D5185m	>30	<1		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon		ASTM D5185m	>50	17		
Potassium	ppm ppm	ASTM D5185m	>20	0		
Water	ppiii	WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt			NONE	NONE		
	scalar	*Visual *Visual		NORML		
Appearance	scalar		NORML	NORML		
Odor	scalar	*Visual	NORML	-		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		0		
Sodium Boron	ppm ppm	ASTM D5185m ASTM D5185m		0 180		
Boron	ppm	ASTM D5185m		180		
Boron Barium	ppm ppm	ASTM D5185m ASTM D5185m		180 <1		
Boron Barium Molybdenum	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m		180 <1 3		
Boron Barium Molybdenum Manganese	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m		180 <1 3 2		
Boron Barium Molybdenum Manganese Magnesium	ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m		180 <1 3 2 3	 	
Boron Barium Molybdenum Manganese Magnesium Calcium	ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m		180 <1 3 2 3 36	 	
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus	ppm ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m		180 <1 3 2 3 36 2066		
Boron Barium Molybdenum Manganese Magnesium Calcium Phosphorus Zinc	ppm ppm ppm ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m ASTM D5185m		180 <1 3 2 3 36 2066 34		

Submitted By: DARRELL ANDES





MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : ML0886255 Received 8450 QUARRY ROAD : 26 Feb 2024 Lab Number : 06101228 MANASSAS, VA Tested : 28 Feb 2024 Unique Number : 10899458 : 28 Feb 2024 - Don Baldridge US 20110 Diagnosed Test Package : MOBCE Contact: DARRELL ANDES Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. dandes@mcclung-logan.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Т: F: (703)393-7844 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: DARRELL ANDES

Page 2 of 2