



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
FLEET
Machine Id
2227066 (S/N 0000)
Component
Diesel Engine
Fluid
NOT GIVEN (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PCA0116253	PCA0104907	---
Sample Date		Client Info		13 Feb 2024	19 Sep 2023	---
Machine Age	hrs	Client Info		604	0	---
Oil Age	hrs	Client Info		604	0	---
Filter Age	hrs	Client Info		0	0	---
Oil Changed		Client Info		N/A	N/A	---
Filter Changed		Client Info		N/A	N/A	---
Sample Status				NORMAL	ABNORMAL	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	40	50	---
Chromium	ppm	ASTM D5185m	>20	<1	<1	---
Nickel	ppm	ASTM D5185m	>4	0	<1	---
Titanium	ppm	ASTM D5185m		0	0	---
Silver	ppm	ASTM D5185m	>3	<1	18	---
Aluminum	ppm	ASTM D5185m	>20	15	47	---
Lead	ppm	ASTM D5185m	>40	<1	2	---
Copper	ppm	ASTM D5185m	>330	173	179	---
Tin	ppm	ASTM D5185m	>15	2	4	---
Vanadium	ppm	ASTM D5185m		0	<1	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	20	▲ 81	---
Potassium	ppm	ASTM D5185m	>20	32	122	---
Fuel	%	ASTM D3524	>5	<1.0	0.3	---
Water		WC Method	>0.2	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	0.4	0.2	---
Nitration	Abs/cm	*ASTM D7624	>20	10.3	10.5	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.7	23.3	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		3	8	---
Boron	ppm	ASTM D5185m		6	199	---
Barium	ppm	ASTM D5185m		0	0	---
Molybdenum	ppm	ASTM D5185m		68	134	---
Manganese	ppm	ASTM D5185m		1	4	---
Magnesium	ppm	ASTM D5185m		884	783	---
Calcium	ppm	ASTM D5185m		1178	1620	---
Phosphorus	ppm	ASTM D5185m		864	689	---
Zinc	ppm	ASTM D5185m		1062	833	---
Sulfur	ppm	ASTM D5185m		2110	2186	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.0	21.8	---
Base Number (BN)	mg KOH/g	ASTM D2896		5.5	8.3	---
Visc @ 100°C	cSt	ASTM D445		10.0	9.3	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PCA0116253 **Received** : 27 Feb 2024
Lab Number : 06101367 **Tested** : 28 Feb 2024
Unique Number : 10899597 **Diagnosed** : 28 Feb 2024 - Don Baldrige
Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

PERDUE FARMS - DILLON
 2047 HWY 9 WEST
 DILLON, SC
 US 29536
 Contact: KEVIN HOOKS
 kevin.hooks@perdue.com
 T: (843)841-8069
 F: (843)841-8070

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)