

Machine Id BELL 830E B93A331EK03009461 Component Diesel Engine Fluid


{not provided} (--- GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0204254		
	Sample Date		Client Info		22 Feb 2024		
	Machine Age	hrs	Client Info		3124		
	Oil Age	hrs	Client Info		3124		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		4		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	<1		
	Nickel	ppm	ASTM D5185m	>4	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m	>20	3		
	Lead	ppm	ASTM D5185m	>40	0		
	Copper	ppm	ASTM D5185m	>330	<1		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon		ASTM D5185m	05	•		
CONTAMINATION	Potassium	ppm	ASTM D5185m		9 3		
There is no indication of any contamination in the oil.	Fuel	ppm	WC Method				
	Water		WC Method		<1.0 NEG		
	Glycol		WC Method	>0.2	NEG		
	Soot %	%	*ASTM D7844	. 2	0		
	Nitration	Abs/cm	*ASTM D7644	>3 >20	5.4		
	Sulfation	Abs/.1mm	*ASTM D7624				
	Silt	scalar	*Visual	NONE	19.5 NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt		*Visual	NONE	NONE		
	Appearance	scalar scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
		304141	Visual	20.2			
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
	Boron	ppm	ASTM D5185m		256		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m		228		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		686		
	Calcium	ppm	ASTM D5185m		1148		
	Phosphorus	ppm	ASTM D5185m		781		
	Zinc	ppm	ASTM D5185m		947		
	Sulfur	ppm	ASTM D5185m		2999		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.0		
	Base Number (BN)	mg KOH/g			9.6		
	Vier C 10000	- 01	AOTA DATE				

Visc @ 100°C cSt

ASTM D445

14.5





Page 2 of 2