WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

[W49929] ZJT00637

Component Hydraulic System

CĂT HYDO (QTS)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0200306		
	Sample Date		Client Info		15 Feb 2024		
	Machine Age	hrs	Client Info		2164		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		9		
	Iron	ppm	ASTM D5185m	>20	4		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	7.0	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>10	<1		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		7		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	210	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	- 20	າ		
		ppm			3 0		
There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.	Potassium	ppm	ASTM D5185m		-		
	Water		WC Method		NEG		
	Particles >4µm		ASTM D7647		609		
	Particles >6µm		ASTM D7647		125		
	Particles >14µm		ASTM D7647		8		
	Particles >21µm		ASTM D7647		2		
	Particles >38µm		ASTM D7647		0		
	Particles >71μm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		16/14/10		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		92		
	Calcium	ppm	ASTM D5185m		101		
	Phosphorus	ppm	ASTM D5185m	1100	547		
	Zinc	ppm	ASTM D5185m		459		
	Sulfur	ppm	ASTM D5185m		1647		
	Sulfur Acid Number (AN)	ppm mg KOH/g	ASTM D5185m ASTM D8045		164 <i>7</i> 0.54		

Contact/Location: DAVID ZIEG - JAMASH





Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0200306 Lab Number : 06101533

Unique Number: 10899763

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received : 27 Feb 2024 **Tested**

: 28 Feb 2024 Diagnosed Test Package : CONST (Additional Tests: PQ)

: 29 Feb 2024 - Jonathan Hester

US 23005 Contact: DAVID ZIEG dzieg@jamesriverequipment.com T: (804)798-6001

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. F: (804)798-0292 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - ASHLAND

ASHLAND, VA

11047 LEADBETTER RD