WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

B93A331EK03009461

Component Front Differential

GEAR OIL SAE 80W90 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm. Please specify the component make and model with your next sample.	Sample Number		Client Info		JR0204259		
	Sample Date		Client Info		22 Feb 2024		
	Machine Age	hrs	Client Info		3124		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		170		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	160		
	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		3		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		22		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	7		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	>.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	1		
The condition of the oil is acceptable for the time in service. Report Id: IAMCHA IWUSCARI 06101948 (Generated: 02/28/2024 22:09:31) Rev: 1	Boron	ppm	ASTM D5185m	400	332		
	Barium	ppm	ASTM D5185m	200	0		
	Molybdenum	ppm	ASTM D5185m	12	<1		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m	12	5		
	Calcium	ppm	ASTM D5185m		17		
	Phosphorus	ppm	ASTM D5185m		1836		
	Zinc	ppm	ASTM D5185m		10		
	Sulfur	ppm	ASTM D5185m		20272		
	Visc @ 40°C	cSt	ASTM D445	143	130		





Certificate L2367

Laboratory Sample No.

Lab Number : 06101948

: JR0204259 Unique Number : 10900178

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Diagnosed Test Package : CONST (Additional Tests: PQ)

: 27 Feb 2024 : 28 Feb 2024 : 28 Feb 2024 - Wes Davis

JRE - CHARLOTTE 9550 STATESVILLE ROAD CHARLOTTE, NC

US 28269

Contact: CHARLOTTE SHOP myoung@jamesriverequipment.com

T: (704)597-0211 F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)