

WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL



BELL B45E B93A645EK03007699

Wet Disc Brake

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	OOM	Client Info	Little/ton	BE0003741		
Resample at the next service interval to monitor.	Sample Date		Client Info		12 Feb 2024		
	Machine Age	hrs	Client Info		4170		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		18		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>20	10		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>10	1		
	Lead	ppm	ASTM D5185m	>10	4		
	Copper	ppm	ASTM D5185m	>75	41		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	7		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	LIGHT		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		6		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		83		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		10		
	Calcium	ppm	ASTM D5185m		1673		
	Phosphorus	ppm	ASTM D5185m		858		
	Zinc	ppm	ASTM D5185m		735		
	Sulfur	ppm	ASTM D5185m		2172		
	Visc @ 40°C	cSt	ASTM D445		35.4		







Report Id: BEFOU005 [WUSCAR] 06101972 (Generated: 02/29/2024 15:57:01) Rev: 1

Laboratory Sample No.

: BE0003741 Lab Number : 06101972 Unique Number : 10900202 Test Package : MOBCE To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Feb 2024 **Tested** : 29 Feb 2024 Diagnosed

: 29 Feb 2024 - Jonathan Hester

US 77064 Contact: Vaughan Phillips vphillips@fourseasons-equip.com T: (800)234-5007

Four Seasons Equipment Inc.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

8111 Mills Road

Houston, TX