

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL




CATERPILLAR 2480

Component
Diesel Engine
Fluid

SHELL 15W40 (--- GAL)

SHELL 15W40 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WC0800410		
	Sample Date		Client Info		26 Feb 2024		
	Machine Age	hrs	Client Info		4659		
	Oil Age	hrs	Client Info		500		
	Filter Age	hrs	Client Info		500		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAD							
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m		11		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m	>15	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>25	5		
	Potassium	ppm	ASTM D5185m		2		
	Fuel	pp	WC Method	>5	- <1.0		
	Water		WC Method		NEG		
	Glycol		WC Method	7 U.L	NEG		
	Soot %	%	*ASTM D7844	>3	0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	8.9		
	Sulfation	Abs/.1mm	*ASTM D7415		18.9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>150	1		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		32		
oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		79		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		260		
	Calcium	ppm	ASTM D5185m		1638		
	Phosphorus	ppm	ASTM D5185m		934		
	Zinc	ppm	ASTM D5185m		1061		
	Sulfur	ppm	ASTM D5185m		3217		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	15.0		
	Base Number (BN)	mg KOH/g	ASTM D2896		6.0		
	Visc @ 100°C	cSt	ASTM D445		12.9		







Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0800410 Lab Number : 06102263

Unique Number : 10900493

Received **Tested** Diagnosed : 27 Feb 2024

: 28 Feb 2024

: 28 Feb 2024 - Wes Davis

Test Package : CONST (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CJ MILLER LLC 2903 DEDE RD FINKSBURG, MD

US 21048 Contact: JOE ROSS jross@cjmillerllc.com T: (410)239-8006

F: (410)239-1051