



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
857-4017

Component
Diesel Engine

Fluid
MOBIL DELVAC 1300 SUPER 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0014853	RPL0005716	---
Sample Date		Client Info		01 Feb 2024	04 Nov 2022	---
Machine Age	mls	Client Info		258922	208869	---
Oil Age	mls	Client Info		11963	34475	---
Filter Age	mls	Client Info		11963	34475	---
Oil Changed		Client Info		Changed	Changed	---
Filter Changed		Client Info		Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	47	72	---
Chromium	ppm	ASTM D5185m	>20	3	4	---
Nickel	ppm	ASTM D5185m	>4	<1	0	---
Titanium	ppm	ASTM D5185m		<1	<1	---
Silver	ppm	ASTM D5185m	>3	<1	0	---
Aluminum	ppm	ASTM D5185m	>20	11	12	---
Lead	ppm	ASTM D5185m	>40	8	13	---
Copper	ppm	ASTM D5185m	>330	3	7	---
Tin	ppm	ASTM D5185m	>15	1	2	---
Vanadium	ppm	ASTM D5185m		<1	<1	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	15	12	---
Potassium	ppm	ASTM D5185m	>20	26	24	---
Fuel		WC Method	>5	<1.0	<1.0	---
Water		WC Method	>0.2	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	0.9	1.2	---
Nitration	Abs/cm	*ASTM D7624	>20	13.0	16.5	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	28.0	36.3	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	2	---
Boron	ppm	ASTM D5185m		29	15	---
Barium	ppm	ASTM D5185m		<1	2	---
Molybdenum	ppm	ASTM D5185m		23	23	---
Manganese	ppm	ASTM D5185m		2	1	---
Magnesium	ppm	ASTM D5185m		706	779	---
Calcium	ppm	ASTM D5185m		1360	1630	---
Phosphorus	ppm	ASTM D5185m		764	793	---
Zinc	ppm	ASTM D5185m		860	1001	---
Sulfur	ppm	ASTM D5185m		3044	3682	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	24.5	36.0	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	5.1	4.6	---
Visc @ 100°C	cSt	ASTM D445	11.9	11.6	13.1	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0014853
Lab Number : 06102371
Unique Number : 10900601
Test Package : FLEET

Received : 27 Feb 2024
Tested : 28 Feb 2024
Diagnosed : 28 Feb 2024 - Wes Davis

RTL PACLEASE - 7001 - Houston
 6300 N. Loop East
 Houston, TX
 US 77026

Contact: RODNEY BRIGGS
 briggsr@rushenterprises.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: