



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 624L 1DW624LTCKF701433

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0201184	JR0182459	JR0164086
Sample Date		Client Info		26 Feb 2024	29 Aug 2023	09 Mar 2023
Machine Age	hrs	Client Info		6007	5529	4700
Oil Age	hrs	Client Info		478	829	436
Filter Age	hrs	Client Info		478	829	436
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	12	9	9
Chromium	ppm	ASTM D5185m	>11	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	5	4	4
Lead	ppm	ASTM D5185m	>26	<1	0	0
Copper	ppm	ASTM D5185m	>26	1	0	<1
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	8	6	6
Potassium	ppm	ASTM D5185m	>20	4	3	3
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.7	8.3	8.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.2	21.1	22.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	2	3	3
Boron	ppm	ASTM D5185m		206	247	225
Barium	ppm	ASTM D5185m		2	0	<1
Molybdenum	ppm	ASTM D5185m		244	248	238
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m		728	885	779
Calcium	ppm	ASTM D5185m		1232	1452	1427
Phosphorus	ppm	ASTM D5185m		788	919	836
Zinc	ppm	ASTM D5185m		975	1144	1034
Sulfur	ppm	ASTM D5185m		2907	3787	3509
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.9	15.7	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.5	8.2	8.9
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	13.4	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0201184

Lab Number : 06102721

Unique Number : 10900951

Test Package : CONST (Additional Tests: TBN)

Received : 28 Feb 2024

Tested : 29 Feb 2024

Diagnosed : 29 Feb 2024 - Wes Davis

JRE - NEW BERN
3816 MARTIN LUTHER KING BLVD
NEW BERN, NC
US 28562

Contact: NEW BERN SHOP

nick.etheridge@jamesriverequipment.com; canastasio@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: