



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[W49984]
 Machine Id
JOHN DEERE 824K 1DW824KXTHF680767
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0200464	JR0199981	JR0180651
Sample Date		Client Info		23 Feb 2024	29 Jan 2024	20 Dec 2023
Machine Age	hrs	Client Info		10186	9797	9291
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ATTENTION	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	6	9	16
Chromium	ppm	ASTM D5185m	>11	<1	1	1
Nickel	ppm	ASTM D5185m	>5	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	5	7	11
Lead	ppm	ASTM D5185m	>26	<1	2	7
Copper	ppm	ASTM D5185m	>26	<1	2	3
Tin	ppm	ASTM D5185m	>4	<1	1	1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	7	8	7
Potassium	ppm	ASTM D5185m	>20	3	6	11
Fuel	%	ASTM D3524	>2.1	<1.0	2.5	4.1
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	7.6	8.1	8.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.7	21.2	22.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	0	<1
Boron	ppm	ASTM D5185m		249	222	200
Barium	ppm	ASTM D5185m		0	0	3
Molybdenum	ppm	ASTM D5185m		246	230	247
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		826	774	782
Calcium	ppm	ASTM D5185m		1391	1231	1344
Phosphorus	ppm	ASTM D5185m		939	886	824
Zinc	ppm	ASTM D5185m		1121	1039	1012
Sulfur	ppm	ASTM D5185m		3388	3010	3223
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.9	15.6	17.4
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.2	8.2	7.5
Visc @ 100°C	cSt	ASTM D445	15.4	12.5	12.2	12.0



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0200464 **Received** : 28 Feb 2024
Lab Number : 06102795 **Tested** : 29 Feb 2024
Unique Number : 10901025 **Diagnosed** : 29 Feb 2024 - Don Baldrige
Test Package : CONST (Additional Tests: FuelDilution, TBN)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)