




WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL


Store 9 - Marietta **FREIGHTLINER 1042**


Component Diesel Engine


SHELL ROTELLA T 15W40 (10	GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		LEC0045344	LEC0045820	LEC0044049
Resample at the next service interval to monitor.	Sample Date		Client Info		20 Feb 2024	11 Jan 2024	16 Oct 2023
	Machine Age	mls	Client Info		1043706	1031410	1001094
	Oil Age	mls	Client Info		10000	10000	10000
	Filter Age	mls	Client Info		10000	10000	10000
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>80	15	16	17
	Chromium	ppm	ASTM D5185m	>5	1	1	1
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1	1	0
	Titanium	ppm	ASTM D5185m		<1	<1	0
	Silver	ppm	ASTM D5185m	>3	0	0	0
	Aluminum	ppm	ASTM D5185m		8	8	13
	Lead	ppm	ASTM D5185m		5	7	4
	Copper	ppm	ASTM D5185m		<1	1	1
	Tin	ppm	ASTM D5185m		<1	1	<1
	Vanadium	ppm	ASTM D5185m		0	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	\I20	9	7	8
CONTAMINATION	Potassium	ppm	ASTM D5185m		16	25	31
There is no indication of any contamination in the oil.	Fuel	ррпп	WC Method		<1.0	<1.0	<1.0
	Water		WC Method		NEG	NEG	NEG
	Glycol		WC Method	70.L	NEG	NEG	NEG
	Soot %	%	*ASTM D7844	\3	0.3	0.4	0.3
	Nitration	Abs/cm	*ASTM D7624	>20	8.7	9.2	8.8
	Sulfation	Abs/.1mm	*ASTM D7415		24.2	24.9	24.4
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water		*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		7	3	4
I EOID CONDITION	Boron	ppm	ASTM D5185m	316	259	243	248
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0	1	0
	Molybdenum	ppm	ASTM D5185m		148	137	127
	Manganese	ppm	ASTM D5185m	1	<1	1	<1
	Magnesium	ppm	ASTM D5185m	24	712	687	690
	Calcium	ppm	ASTM D5185m	2292	1610	1477	1606
	Phosphorus	ppm	ASTM D5185m		736	704	723
	Zinc	ppm	ASTM D5185m		928	887	923
	Sulfur	ppm	ASTM D5185m		2657	2572	2561
	Oxidation	Abs/.1mm	*ASTM D7414		18.3	18.9	18.6
	Base Number (BN)				7.7	7.4	8.1
	Visc @ 100°C	cSt	ASTM D445		13.2	13.2	13.3
	0						. 3.0













Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 06102807

Unique Number : 10901037 Test Package : CONST (Additional Tests: TBN)

Received : LEC0045344 **Tested**

: 28 Feb 2024 Diagnosed

: 29 Feb 2024

: 29 Feb 2024 - Don Baldridge

US 26346 Contact: CHRIS PETROVICH chrispetrovich@halldrilling.com T: (304)869-3404

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (304)869-3408

HALL DRILLING LLC

ELLENBORO, WV

PO BOX 249