



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
920085-205325

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0087914	GFL0060283	GFL0060285
Sample Date		Client Info		27 Feb 2024	12 Dec 2022	22 Sep 2022
Machine Age	hrs	Client Info		0	7942	7800
Oil Age	hrs	Client Info		600	580	590
Filter Age	hrs	Client Info		600	580	590
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	63	17	13
Chromium	ppm	ASTM D5185m	>20	5	1	<1
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	10	2	2
Lead	ppm	ASTM D5185m	>40	0	<1	2
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	3	4
Potassium	ppm	ASTM D5185m	>20	13	5	6
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	2	1.3	1.1
Nitration	Abs/cm	*ASTM D7624	>20	11.8	9.7	9.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.2	22.3	22.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	2
Boron	ppm	ASTM D5185m	0	2	1	2
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	62	58	60
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	970	1006	957
Calcium	ppm	ASTM D5185m	1070	1069	1111	1102
Phosphorus	ppm	ASTM D5185m	1150	986	1010	983
Zinc	ppm	ASTM D5185m	1270	1253	1320	1354
Sulfur	ppm	ASTM D5185m	2060	2958	3482	3314
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.9	16.4	16.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.8	10.0	9.7
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	14.4	14.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0087914
Lab Number : 06102833
Unique Number : 10901063
Test Package : FLEET

Received : 28 Feb 2024
Tested : 29 Feb 2024
Diagnosed : 29 Feb 2024 - Don Baldrige

GFL Environmental - 859 - Bay City
 700 Avenue F
 Bay City, TX
 US 77414

Contact: JONATHON BROWN
 jonathon.brown@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: