
WEAR CONTAMINATION FLUID CONDITION

NORMAL ABNORMAL NORMAL

MATTEI 10009479-2019 (S/N ASU 296)

Component Compressor

ROTOROIL 8000 (2 QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
No corrective action is recommended at this time. We recommend an early resample to monitor this condition.	Sample Number		Client Info		AN37702	AN37340	
	Sample Date		Client Info		19 Feb 2024	31 Jul 2023	
	Machine Age	hrs	Client Info		3860	2476	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		N/A	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				ABNORMAL	ABNORMAL	
WEAR	Iron	ppm	ASTM D5185m	>50	40	33	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0	0	
	Nickel	ppm	ASTM D5185m		<1	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	0	<1	
	Lead	ppm	ASTM D5185m	>25	0	0	
	Copper	ppm	ASTM D5185m	>50	0	<1	
	Tin	ppm	ASTM D5185m	>15	<1	0	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	NONE	▲ MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	122	▲ 104	
Elemental level of silicon (Si) above normal. The water content is negligible.	Potassium	ppm	ASTM D5185m	>20	0	1	
	Water	%	ASTM D6304	>0.1	0.041	0.052	
	ppm Water	ppm	ASTM D6304	>1000	410	522.2	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2	9	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		<1	0	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		0	0	
	Manganese	ppm	ASTM D5185m		0	<1	
	Magnesium	ppm	ASTM D5185m		0	0	
	Calcium	ppm	ASTM D5185m		0	0	
	Phosphorus	ppm		884	871	878	
	Zinc	ppm	ASTM D5185m		3	16	
	Sulfur	ppm	ASTM D5185m		102	383	
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.19	0.28	
Report Id: MATTELIWUSCARI 06103057 (Generated: 03/01/2024 13:23:15) Rev: 1	Visc @ 40°C	cSt	ASTM D445		72.4	86.5 ARTY WARD	
					" OCAHOD: IV		N// A I I I I I







Certificate L2367

Laboratory Sample No.

: AN37702 Lab Number : 06103057 Unique Number: 10901287 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 Feb 2024 : 01 Mar 2024 **Tested**

Diagnosed

: 01 Mar 2024 - Jonathan Hester

US 21133 Contact: MARTY WARD jward@matteicomp.com T: (410)521-7020

RANDALLSTOWN, MD

9635 LIBERTY ROAD, SUITE E

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (410)521-7024