



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
CATERPILLAR GM02
Component
Biogas Engine
Fluid
MAHLER Q8 Mahler G8 SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0870512	WC0870565	WC0870511
Sample Date		Client Info		27 Feb 2024	20 Feb 2024	14 Feb 2024
Machine Age	hrs	Client Info		67980	67821	0
Oil Age	hrs	Client Info		199	20	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>45	26	22	▲ 98
Chromium	ppm	ASTM D5185m	>2	<1	<1	1
Nickel	ppm	ASTM D5185m	>2	<1	0	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>5	0	<1	0
Aluminum	ppm	ASTM D5185m	>10	2	2	1
Lead	ppm	ASTM D5185m	>5	<1	0	<1
Copper	ppm	ASTM D5185m	>14	<1	1	1
Tin	ppm	ASTM D5185m	>13	1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>200	124	27	24
Potassium	ppm	ASTM D5185m	>20	0	2	<1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0.1
Nitration	Abs/cm	*ASTM D7624	>20	5.9	4.5	4.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.0	14.9	14.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	0	2
Boron	ppm	ASTM D5185m		<1	0	<1
Barium	ppm	ASTM D5185m		0	0	5
Molybdenum	ppm	ASTM D5185m		0	<1	1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		3	3	3
Calcium	ppm	ASTM D5185m		1446	1277	1088
Phosphorus	ppm	ASTM D5185m		330	402	334
Zinc	ppm	ASTM D5185m		436	409	366
Sulfur	ppm	ASTM D5185m		1816	2002	1739
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.6	9.1	9.0
Acid Number (AN)	mg KOH/g	ASTM D8045		0.877	1.76	0.37
Base Number (BN)	mg KOH/g	ASTM D2896	8.0	4.40	5.82	6.52
Visc @ 100°C	cSt	ASTM D445	13.2	13.5	13.2	13.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0870512
Lab Number : 06103169
Unique Number : 10901399
Test Package : MOB 2

Received : 28 Feb 2024
Tested : 29 Feb 2024
Diagnosed : 01 Mar 2024 - Sean Felton

OAK GROVE KS
 1150 E 700TH AVE
 ARCADIA, KS
 US 66711

Contact: KALEB WEAVER
 kaleb.weaver@cubedistrictenergy.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: