

WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL



[74848 LAKE CONWAY] VOLVO L20H 1220189

Front Axle

			GAL)				
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP446888	VCP346609	
	Sample Date		Client Info		20 Feb 2024	02 Mar 2022	
	Machine Age	hrs	Client Info		3401	2089	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Not Changd	Changed	
	Filter Changed		Client Info		Not Changd	Not Changd	
	Sample Status				NORMAL	ATTENTION	
VEAR	Iron	ppm	ASTM D5185m	>500	166	362	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	2	6	
	Nickel	ppm	ASTM D5185m	>10	<1	<1	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>30	<1	2	
	Lead	ppm	ASTM D5185m	>50	0	<1	
	Copper	ppm	ASTM D5185m	>120	1	3	
	Tin	ppm	ASTM D5185m	>20	0	0	
	Vanadium	ppm	ASTM D5185m		0	<1	
	White Metal	scalar	*Visual	NONE	NONE	LIGHT	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Ciliana		ACTM DE10E			40	
CONTAMINATION	Silicon	ppm	ASTM D5185m		6 1	13 2	
There is no indication of any contamination in the oil.	Potassium Water	ppm	ASTM D5185m WC Method		NEG	NEG	
	Silt	asalar	*Visual		NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
I LUD CONDITION	0 "		40TM D5405				
FLUID CONDITION	Sodium	ppm	ASTM D5185m	444	2	9	
The condition of the oil is acceptable for the time in service.	Boron Barium	ppm	ASTM D5185m ASTM D5185m		133	117 0	
		ppm	ASTM D5185m		0 4	<1	
	Molybdenum Manganese	ppm	ASTM D5185m		6	20	
	Magnesium	ppm	ASTM D5185m		19	5	
	Calcium	ppm	ASTM D5185m		469	3764	
	Phosphorus	ppm	ASTM D5185m		1104	1265	
	Zinc	ppm	ASTM D5185m		220	1623	
	Sulfur	ppm	ASTM D5185m	20179	30671	3619	
	Visc @ 40°C	cSt	ASTM D445		258	52.0	





Laboratory Sample No.

: VCP446888 Lab Number : 06103371 Unique Number : 10901601 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 Feb 2024 : 29 Feb 2024 **Tested**

: 29 Feb 2024 - Wes Davis Diagnosed

ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC

8418 PALM RIVER ROAD TAMPA, FL US 33619

Contact: KENNY HANEY khaney@flaglerce.com T: (813)630-0077

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. F: (813)630-2233

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)