

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

## 24B1504 PEL-005a

New (Unused) Oil

NOT GIVEN (--- GAL)

	_				$\langle \cdot \rangle$	V	
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL0000904		
	Sample Date		Client Info		20 Feb 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
					·····		
CONTAMINATION	Silicon	ppm	ASTM D5185m		8		
	Potassium	ppm	ASTM D5185m	>20	1		
	Water		WC Method		NEG		
	Particles >4µm		ASTM D7647	>5000	2261		
	Particles >6µm		ASTM D7647	>1300	531		
	Particles >14μm		ASTM D7647	>160	25		
	Particles >21μm		ASTM D7647	>40	6		
	Particles >38μm		ASTM D7647	>10	0		
	Particles >71μm		ASTM D7647	>3	0		
	Oil Cleanliness		ISO 4406 (c)	>19/17/14	18/16/12		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual		NEG		
FLUID CONDITION	Cadium		ACTM DE10Em				
	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		110		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		<1		
	Calcium	ppm	ASTM D5185m		1		
	Phosphorus	ppm	ASTM D5185m		29		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		11830		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.046		
	Visc @ 40°C	cSt	ASTM D445		32.62		
	Visc @ 100°C	cSt	ASTM D445		6.72		
	Viscosity Index (VI)	Caala	ASTM D2270		169		





Certificate L2367

Laboratory Sample No.

: HPL0000904 Lab Number : 06103429 Unique Number: 10901659

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 Feb 2024 **Tested** : 04 Mar 2024

: 04 Mar 2024 - Jonathan Hester Diagnosed Test Package : MOB 2 ( Additional Tests: FT-IR, KV100, PrtCount, VI )

HIGH PERFORMANCE LUBRICANTS LLC 500 S SPRUCE ST MANTENO, IL US 60950

Contact: DAVID WARD sampledata@hplubricants.com T: (815)468-3535

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: