



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
(YA141202) Whiteville NC
Machine Id
10824
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (6 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please note that this is a corrected copy for data entry updates.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0083379	GFL0083372	GFL0083356
Sample Date		Client Info		28 Feb 2024	17 Nov 2023	11 Sep 2023
Machine Age	hrs	Client Info		0	10751	90580
Oil Age	hrs	Client Info		0	600	600
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	23	22	4
Chromium	ppm	ASTM D5185m	>5	1	<1	0
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m	>2	<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	4	3	0
Lead	ppm	ASTM D5185m	>25	0	<1	0
Copper	ppm	ASTM D5185m	>100	<1	2	<1
Tin	ppm	ASTM D5185m	>4	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	7	5
Potassium	ppm	ASTM D5185m	>20	1	2	▲ 63
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.5	0.6	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.9	9.1	6.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.7	20.0	18.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		52	70	▲ 134
Boron	ppm	ASTM D5185m	0	2	2	7
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	63	64	63
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	1023	1012	980
Calcium	ppm	ASTM D5185m	1070	1052	1168	1089
Phosphorus	ppm	ASTM D5185m	1150	1079	1120	1106
Zinc	ppm	ASTM D5185m	1270	1354	1365	1320
Sulfur	ppm	ASTM D5185m	2060	3473	3299	4049
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.4	16.4	13.6
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.1	8.6	9.6
Visc @ 100°C	cSt	ASTM D445	15.4	14.0	13.8	13.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0083379
Lab Number : 06104036
Unique Number : 10902266
Test Package : FLEET

Received : 29 Feb 2024
Tested : 05 Mar 2024
Diagnosed : 05 Mar 2024 - Doug Bogart

GFL Environmental - 108 - Whiteville
 5240 James B White Hwy South
 Whiteville, NC
 US 28472
 Contact: Victor McGee
 victor.mcgee@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: