



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 210G 1FF210GXHMF529661
Component
Diesel Engine
Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0202736	JR0190865	JR0133193
Sample Date		Client Info		27 Feb 2024	29 Oct 2023	14 Jul 2022
Machine Age	hrs	Client Info		2500	2058	507
Oil Age	hrs	Client Info		442	1551	507
Filter Age	hrs	Client Info		0	0	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	37	25	6
Chromium	ppm	ASTM D5185m	>11	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	4	3	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>31	4	2	3
Lead	ppm	ASTM D5185m	>26	<1	1	<1
Copper	ppm	ASTM D5185m	>26	15	28	46
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	7	4	7
Potassium	ppm	ASTM D5185m	>20	2	2	2
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.5	6.7	7.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.3	18.9	21.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	2	4	<1
Boron	ppm	ASTM D5185m		172	9	303
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		233	54	252
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		973	833	706
Calcium	ppm	ASTM D5185m		1631	1071	1398
Phosphorus	ppm	ASTM D5185m		934	982	851
Zinc	ppm	ASTM D5185m		1295	1126	1019
Sulfur	ppm	ASTM D5185m		3327	2697	3438
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	14.7	15.6
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	7.9	8.5	10.9
Visc @ 100°C	cSt	ASTM D445	15.4	13.3	14.0	14.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0202736 **Received** : 29 Feb 2024
Lab Number : 06104165 **Tested** : 29 Feb 2024
Unique Number : 10902395 **Diagnosed** : 02 Mar 2024 - Don Baldrige
Test Package : CONST (Additional Tests: TBN)

JRE - GARNER
 4161 AUBURN CHURCH RD
 GARNER, NC
 US 27529

Contact: RALEIGH SHOP
 sean.betts@jamesriverequipment.com; catherine.anastasio@wearcheck.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (919)614-2260
 F: (919)779-5432