
**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 


Machine Id 10757


Component Diesel Engine


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		GFL0104032	GFL0091187	GFL008219
Resample at the next service interval to monitor.	Sample Date		Client Info		19 Feb 2024	06 Oct 2023	23 Jun 202
	Machine Age	hrs	Client Info		52047	17363	17036
	Oil Age	hrs	Client Info		17968	17363	17036
	Filter Age	hrs	Client Info		650	650	650
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
VEAR	Iron	ppm	ASTM D5185m	>100	27	18	12
	Chromium	ppm	ASTM D5185m	>20	1	<1	<1
All component wear rates are normal.	Nickel	ppm	ASTM D5185m	>4	<1	0	0
	Titanium	ppm	ASTM D5185m		0	0	0
	Silver	ppm	ASTM D5185m	>3	0	0	0
	Aluminum	ppm	ASTM D5185m	>20	4	3	4
	Lead	ppm	ASTM D5185m	>40	<1	0	0
	Copper	ppm	ASTM D5185m	>330	2	<1	<1
	Tin	ppm	ASTM D5185m	>15	<1	0	<1
	Vanadium	ppm	ASTM D5185m		<1	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	7	4	4
	Potassium	ppm	ASTM D5185m	>20	2	3	2
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0	<1.0	<1.0
	Water		WC Method	>0.2	NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	0.7	0.4	0.3
	Nitration	Abs/cm	*ASTM D7624	>20	11.4	7.9	8.4
	Sulfation	Abs/.1mm	*ASTM D7415	>30	21.7	20.2	19.5
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4	4	2
	Boron	ppm	ASTM D5185m	0	19	22	50
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m	0	0	0	0
	Molybdenum	ppm	ASTM D5185m	60	77	63	77
	Manganese	ppm	ASTM D5185m	0	<1	<1	<1
	Magnesium	ppm	ASTM D5185m	1010	741	838	418
	Calcium	ppm	ASTM D5185m		1806	1240	1758
	Phosphorus	ppm	ASTM D5185m	1150	1000	942	1044
	Zinc	ppm	ASTM D5185m		1509	1182	1272
	Sulfur	ppm	ASTM D5185m	2060	3652	2999	4383
	Oxidation	Abs/.1mm	*ASTM D7414	>25	18.5	16.2	15.2
	Base Number (BN)	mg KOH/g	ASTM D2896	9.8	6.0	8.5	8.5
	Visc @ 100°C	cSt		15.4	13.8	13.7	14.0
















Certificate L2367

Laboratory Sample No.

: GFL0104032 Lab Number : 06104202 Unique Number : 10902432

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 29 Feb 2024

: 01 Mar 2024 **Tested** : 01 Mar 2024 - Wes Davis Diagnosed

GFL Environmental - 015 - Columbia

7800 Farrow Road Columbia, SC US 29203-3219

Contact: NOEL MATTHEWS nmatthewsjr@gflenv.com

T: (803)935-0249 F: (803)935-0244

Test Package : FLEET To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)