

WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL ATTENTION

Store 3 - Norton

JOHN DEERE 853M 1T0853MXAKF343716

Right Propel Gearbox


JOHN DEERE GL-5 80W90 (2 GAL)

JOHN DEERE GL-5 80W90 (2 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0045185	LEC0042718	LEC003853
	Sample Date		Client Info		27 Feb 2024	30 Aug 2023	20 Feb 2023
	Machine Age	hrs	Client Info		3050	2577	2083
	Oil Age	hrs	Client Info		473	494	507
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				ATTENTION	ATTENTION	ATTENTION
WEAR	PQ		ASTM D8184		66	40	47
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>1250	89	71	70
	Chromium	ppm	ASTM D5185m	>10	<1	1	<1
	Nickel	ppm	ASTM D5185m	>10	0	0	0
	Titanium	ppm	ASTM D5185m		0	<1	0
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m		4	1	<1
	Lead	ppm	ASTM D5185m		<1	<1	0
	Copper	ppm	ASTM D5185m		1	4	<1
	Tin	ppm	ASTM D5185m		0	1	0
	Vanadium	ppm	ASTM D5185m		0	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	MODE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m		22	6	6
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	0	<1	0
	Water		WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	1	0
The oil viscosity is lower than normal. This plus the additive levels	Boron	ppm	ASTM D5185m		<u> </u>	44	6
indicates the addition of a different brand, or type of oil. Confirm oil type.	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		0	7	<1
	Manganese	ppm	ASTM D5185m		<1	1	<1
	Magnesium	ppm	ASTM D5185m		88	154	7 1
	Calcium	ppm	ASTM D5185m		3101	3261	_ 2058
	Phosphorus	ppm	ASTM D5185m		948	1 019	662
	Zinc	ppm	ASTM D5185m		1123	1189	679
	Sulfur	ppm	ASTM D5185m		3300	4878	8891
	Vian (2) 4000	- 0+	A OTA A DA 4 E		6 50 4	F0.0	75.7

Visc @ 40°C

cSt

ASTM D445





Laboratory Sample No.

Lab Number : 06104579 Unique Number : 10902809

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0045185

Received Tested Diagnosed

: 29 Feb 2024 :01 Mar 2024

: 04 Mar 2024 - Don Baldridge

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL KendalLeanne@lec1.com

T:

F: (740)373-5570