WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



[SCHNITZER STEEL] Machine Id LIEBHERR LH30M 137421-1253

Component Diesel Engine

DIESEL ENGINE OIL SAE 5W30) (GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TEOOMMENDATION	Sample Number	OOM	Client Info	Little / toll	LHMC131012		
Resample at the next service interval to monitor.	Sample Date		Client Info		22 Feb 2024		
	Machine Age	hrs	Client Info		4059		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAD	lvan		ACTM DE10Em	. 66			
WEAR	Iron	ppm	ASTM D5185m		1		
All component wear rates are normal.	Chromium Nickel	ppm	ASTM D5185m		<1		
		ppm	ASTM D5185m	>4	<1		
	Titanium	ppm	ASTM D5185m	. 0	0		
	Silver	ppm	ASTM D5185m ASTM D5185m		0		
	Aluminum Lead	ppm			2		
	Copper	ppm	ASTM D5185m ASTM D5185m		<1 2		
	Tin	ppm	ASTM D5185m				
	Vanadium	ppm	ASTM D5185m	>4	<1 <1		
	White Metal	ppm scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
		Scalai	Visuai	INOINL	INOINE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>15	6		
	Potassium	ppm	ASTM D5185m	>20	2		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	10.4		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
TESIS CONSTITION	Boron	ppm	ASTM D5185m	250	70		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		43		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	450	711		
	Calcium	ppm	ASTM D5185m		1340		
	Phosphorus	ppm	ASTM D5185m	1150	729		
	Zinc	ppm	ASTM D5185m	1350	906		
	Sulfur	ppm	ASTM D5185m	4250	1566		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	21.2		
	Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.6		
	Visc @ 100°C	cSt	ASTM D445	10.9	11.7		





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LHMC131012

Lab Number : 06104955 Unique Number : 10903185

Tested Diagnosed

Received

: 29 Feb 2024

: 01 Mar 2024

: 01 Mar 2024 - Wes Davis

Test Package : MOB 1 (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

RECO EQUIPMENT INC

8075 PRODUCTION DRIVE FLORENCE, KY

US 41042 Contact: ALLEN BRAY abray@recoequip.com

T: F: (859)727-7974

Contact/Location: ALLEN BRAY - LEC0082