



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
Y.S. CHI
Machine Id
[Y.S. CHI] 006 503877-6
Component
Starboard Reduction Gear
Fluid
CHEVRON MEROPA 320 (170 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0064554	MW0064534	MW0061232
Sample Date		Client Info		01 Feb 2024	01 Jan 2024	01 Dec 2023
Machine Age	hrs	Client Info		30916	30200	24037
Oil Age	hrs	Client Info		1536	11523	10757
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	26	29	27
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	2	2
Lead	ppm	ASTM D5185m	>100	5	4	3
Copper	ppm	ASTM D5185m	>50	5	4	4
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	<1	<1	0
Potassium	ppm	ASTM D5185m	>20	1	2	2
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	0	0
Boron	ppm	ASTM D5185m	20	7	8	8
Barium	ppm	ASTM D5185m		1	0	0
Molybdenum	ppm	ASTM D5185m	0	0	<1	<1
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		1	1	1
Calcium	ppm	ASTM D5185m	25	10	12	11
Phosphorus	ppm	ASTM D5185m	235	218	251	252
Zinc	ppm	ASTM D5185m		24	15	13
Sulfur	ppm	ASTM D5185m		5655	5837	6267
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	0.49	0.36	0.38
Visc @ 40°C	cSt	ASTM D445	304	317	315	313



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0064554

Lab Number : 06105362

Unique Number : 10903592

Test Package : MAR 2

Received : 29 Feb 2024

Tested : 02 Mar 2024

Diagnosed : 02 Mar 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: ANTHONY VAN CURA

anthony.vancura@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)