



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
PETERBILT 1248 (S/N 433699)
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (11 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		KFS0004039	KFS0002030	KFS0002029
Sample Date		Client Info		25 Feb 2024	05 Jan 2024	30 Sep 2023
Machine Age	mls	Client Info		710709	697606	676777
Oil Age	mls	Client Info		710709	697606	676777
Filter Age	mls	Client Info		0	20829	22000
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>110	22	34	34
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	1	0
Lead	ppm	ASTM D5185m	>45	1	1	5
Copper	ppm	ASTM D5185m	>85	<1	<1	3
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	5	10	12
Potassium	ppm	ASTM D5185m	>20	2	2	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.4	0.4
Nitration	Abs/cm	*ASTM D7624	>20	7.5	9.3	9.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.3	19.8	20.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	0
Boron	ppm	ASTM D5185m	0	6	4	6
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	63	67	82
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	911	970	1106
Calcium	ppm	ASTM D5185m	1070	1033	1130	1226
Phosphorus	ppm	ASTM D5185m	1150	1015	1100	1282
Zinc	ppm	ASTM D5185m	1270	1260	1286	1714
Sulfur	ppm	ASTM D5185m	2060	3033	2994	5714
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	15.8	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	10.08	9.11	9.52
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.4	14.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KFS0004039
Lab Number : 06105439
Unique Number : 10903669
Test Package : MOB 2
Received : 29 Feb 2024
Tested : 01 Mar 2024
Diagnosed : 01 Mar 2024 - Wes Davis

QUALITY TRAILER SERVICE AND SALES INC
 6280 LEEVILLE PIKE
 LEBANON, TN
 US 37090
 Contact: BONNIE MCCRARY
 airbonnie6280@gmail.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)