



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**(BC30861)**  
Machine Id  
**4690M**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0108821</b>	GFL0105604	GFL0101409
Sample Date		Client Info		<b>28 Feb 2024</b>	13 Dec 2023	25 Nov 2023
Machine Age	hrs	Client Info		<b>16108</b>	15553	15441
Oil Age	hrs	Client Info		<b>15553</b>	15441	2600
Filter Age	hrs	Client Info		<b>15553</b>	15441	2600
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	ABNORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	<b>8</b>	34	27
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>3</b>	4	3
Lead	ppm	ASTM D5185m	>40	<b>0</b>	<1	0
Copper	ppm	ASTM D5185m	>330	<b>&lt;1</b>	3	10
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	0	<1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>4</b>	6	10
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	<1	▲ 102
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	▲ 0.06
Soot %	%	*ASTM D7844	>6	<b>0.3</b>	0.8	0.7
Nitration	Abs/cm	*ASTM D7624	>20	<b>5.4</b>	11.8	11.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>17.8</b>	24.5	23.5
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>16</b>	7	● 272
Boron	ppm	ASTM D5185m	0	<b>3</b>	7	18
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>61</b>	59	74
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	<1
Magnesium	ppm	ASTM D5185m	1010	<b>948</b>	1037	901
Calcium	ppm	ASTM D5185m	1070	<b>1005</b>	1194	1012
Phosphorus	ppm	ASTM D5185m	1150	<b>1074</b>	1076	963
Zinc	ppm	ASTM D5185m	1270	<b>1259</b>	1269	1226
Sulfur	ppm	ASTM D5185m	2060	<b>3319</b>	2673	2563
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>13.2</b>	24.1	21.5
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>9.1</b>	5.3	7.0
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.3</b>	14.0	13.8



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0108821  
**Lab Number** : 06105719  
**Unique Number** : 10903949  
**Test Package** : FLEET

**Received** : 01 Mar 2024  
**Tested** : 01 Mar 2024  
**Diagnosed** : 01 Mar 2024 - Wes Davis

**GFL Environmental - 415 - Michigan East**  
 6200 Elmridge  
 Sterling Heights, MI  
 US 48313  
 Contact: Frank Wolak  
 fwolak@gflenv.com  
 T: (586)825-9514  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)