



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**4653M**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (5 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0115055</b>	GFL0097686	GFL0097671
Sample Date		Client Info		<b>26 Feb 2024</b>	18 Dec 2023	11 Oct 2023
Machine Age	hrs	Client Info		<b>17546</b>	16960	16414
Oil Age	hrs	Client Info		<b>586</b>	546	151
Filter Age	hrs	Client Info		<b>586</b>	546	151
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	ABNORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	<b>10</b>	15	▲ 94
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	0	3
Nickel	ppm	ASTM D5185m	>2	<b>0</b>	0	<1
Titanium	ppm	ASTM D5185m	>2	<b>0</b>	0	<1
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	<1	6
Lead	ppm	ASTM D5185m	>40	<b>0</b>	0	0
Copper	ppm	ASTM D5185m	>330	<b>&lt;1</b>	<1	6
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	0	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	<1
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>4</b>	5	10
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	0	4
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>6	<b>0.4</b>	0.4	1.4
Nitration	Abs/cm	*ASTM D7624	>20	<b>9.2</b>	9.1	18.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>20.5</b>	20.4	33.3
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>7</b>	13	● 100
Boron	ppm	ASTM D5185m	0	<b>3</b>	1	5
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>54</b>	45	65
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	1
Magnesium	ppm	ASTM D5185m	1010	<b>891</b>	833	965
Calcium	ppm	ASTM D5185m	1070	<b>951</b>	998	1106
Phosphorus	ppm	ASTM D5185m	1150	<b>962</b>	835	1007
Zinc	ppm	ASTM D5185m	1270	<b>1231</b>	1108	1334
Sulfur	ppm	ASTM D5185m	2060	<b>2723</b>	2553	2365
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>18.1</b>	18.3	40.6
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>7.0</b>	7.3	4.1
Visc @ 100°C	cSt	ASTM D445	15.4	<b>14.0</b>	13.9	16.9



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0115055  
**Lab Number** : 06105845  
**Unique Number** : 10909342  
**Test Package** : FLEET

**Received** : 01 Mar 2024  
**Tested** : 02 Mar 2024  
**Diagnosed** : 02 Mar 2024 - Wes Davis

**GFL Environmental - 405 - Arbor Hills**  
 7400 Napier Rd  
 NORTHVILLE, MI  
 US 48168

Contact: Anthony Hopkins  
 ahopkins@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: