



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
(BD56625) {UNASSIGNED}
Machine Id
711049
Component
1 Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (7 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0106708	GFL0097685	GFL0097703
Sample Date		Client Info		22 Feb 2024	20 Dec 2023	19 Oct 2023
Machine Age	hrs	Client Info		5766	5169	4583
Oil Age	hrs	Client Info		597	586	539
Filter Age	hrs	Client Info		597	586	539
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	18	30	59
Chromium	ppm	ASTM D5185m	>20	1	2	3
Nickel	ppm	ASTM D5185m	>2	0	1	2
Titanium	ppm	ASTM D5185m	>2	0	<1	<1
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	3	4
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	2	2	6
Tin	ppm	ASTM D5185m	>15	<1	1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	4	7
Potassium	ppm	ASTM D5185m	>20	2	2	7
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.5	0.5	0.7
Nitration	Abs/cm	*ASTM D7624	>20	8.9	8.9	10.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.5	19.6	22.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	6	11
Boron	ppm	ASTM D5185m	0	3	1	1
Barium	ppm	ASTM D5185m	0	0	0	5
Molybdenum	ppm	ASTM D5185m	60	52	56	58
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	859	964	854
Calcium	ppm	ASTM D5185m	1070	911	1078	1054
Phosphorus	ppm	ASTM D5185m	1150	922	1051	974
Zinc	ppm	ASTM D5185m	1270	1186	1246	1175
Sulfur	ppm	ASTM D5185m	2060	2667	3087	2422
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.6	17.1	21.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.7	6.7	6.0
Visc @ 100°C	cSt	ASTM D445	15.4	13.6	13.1	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0106708
 Lab Number : 06105876
 Unique Number : 10909373
 Test Package : FLEET

Received : 01 Mar 2024
 Tested : 02 Mar 2024
 Diagnosed : 02 Mar 2024 - Wes Davis

GFL Environmental - 405 - Arbor Hills
 7400 Napier Rd
 NORTHVILLE, MI
 US 48168

Contact: Anthony Hopkins
 ahopkins@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: