
WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

JOHN DEERE 750L 1T0750LXAPF450316

Right Final Drive

{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0204775		
	Sample Date		Client Info		02 Mar 2024		
	Machine Age	hrs	Client Info		635		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	187		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	76		
	Chromium	ppm	ASTM D5185m	>9	<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		1		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	11		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Water			>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		<1		
	Barium	ppm	ASTM D5185m		5		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		102		
	Calcium	ppm	ASTM D5185m		3355		
	Phosphorus	ppm	ASTM D5185m		971		
	Zinc Sulfur	ppm	ASTM D5185m ASTM D5185m		1220		
	Visc @ 40°C	ppm cSt	ASTM D5185m		3440 53.7		
B	VISC @ 40°C	COL	A311VI D443		53.7		





Laboratory Sample No.

: JR0204775 **Lab Number** : 06106378 Unique Number : 10909875

Test Package : CONST (Additional Tests: PQ)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 01 Mar 2024 : 04 Mar 2024

Tested : 05 Mar 2024 - Sean Felton Diagnosed

JRE - GREENSBORO 411 SOUTH REGIONAL ROAD GREENSBORO, NC US 27409

Contact: JUSTIN WILLIAMS justin.williams@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (336)668-2762

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (336)665-9556